

| | | |
|---|-----------|---|
| Accompanying Technical Documentation | CE | Declaration of Performance DoP n. XXF040 |
|---|-----------|---|

1. Unique identification code of the product -type:

| | |
|---------------|----------------------|
| XXF040 | VAPORFOIL 040 |
|---------------|----------------------|

2. Intended uses:

| Harmonised technical spec. | Intended uses |
|-----------------------------------|------------------------------------|
| EN 13984 | Water Vapor control Layer – Type A |
| EN 13967 | Damp proof sheet – Type A |

3. Name of manufacturer: IMPER ITALIA S.r.l. – Via Rita Atria 9, 10079 MAPPANO (TO) – Italy

4. Authorised Representative: n.a.

5. Systems of assessment and verification of constancy of performance of the construction product:

| Harmonised technical spec | Systems of assessment and verification of constancy of performance of the product: |
|----------------------------------|---|
| EN 13984 | AVCP 3 |
| EN 13967 | AVCP 3 |

6a. This DOP is for construction products falling within the scope of the following harmonized standards:

| Harmonised technical spec | |
|----------------------------------|--|
| EN 13984 | The notified laboratory ID. 0987 carried out initial tests of type (on sampling carried out by the manufacturer) |
| EN 13967 | The notified Organism ID. 1370 has issued the certificate of Conformity of the factory production control |

6b. European technical assessment: n.a.

| | | |
|---|-----------|---|
| Accompanying Technical Documentation | CE | Declaration of Performance DoP n. XXF040 |
|---|-----------|---|

7. Declared performances:

| Essential characteristics | Method EN | U.M. | Performances | Note | Harmonised technical spec. |
|--|--|-------------------|--------------|---------------------|----------------------------|
| Nominal thickness | 1849-2 | mm | 0.40 | - | EN 13984 EN 13967 |
| Reaction to fire | 11925-2 | Euroclasse | F | (as per EN 13501-1) | |
| Watertightness (60 kPa) | 1928/A | - | Pass | - | |
| Tear resistance L/T | 12310-1 | N | ≥ 80 / 80 | limit value | |
| Tensile strenght L/T | 12311-2B | N/mm ² | ≥ 14 / 13 | limit value | |
| Elongation at break L/T | 12311-2B | % | ≥ 450 / 500 | limit value | |
| Resistance to static loading | 12730/B | Kg | ≥ 15 | limit value | |
| Permeability to water vapour (μ) | 1931 | - | 240.000 | ± 70.000 | |
| Durability | | | | | |
| - Watertightness after artificial aging (70 ° C / 84 days) | 1296-1928/A | - | Pass | - | |
| - Watertightness 2 kPa after chemical exposure ("milk of lime" 23 ° C / 28 days) | 1847-1928/A | - | Pass | - | |
| Dangerous substances | The product does not intentionally contain flame retardants, resins, glues and SVHC substances referred to in the most recent Candidate List published on the ECHA website | | | | |

8. Appropriate technical documentation and/or specific technical documentation: ATD01-SHEIF

Mappano, 21/11/2025

Legale rappresentante



Sede Operativa - Stabilimento di Mappano

Via Rita Atria, 9 - 10079 Mappano (TO) Italia
Tel (+39) 011 222.54.99 - Fax (+39) 011 262.51.87
commercialeitalia@imper.it

Stabilimento di Marano Ticino

Via Sempione, 8 - 28040 Marano Ticino (NO) Italia
Tel (+39) 0321 970.16/17 - Fax (+39) 0321 97.226
marano@imper.it

Export Department

Via Rita Atria, 9 - 10079 Mappano (TO) Italia
Tel (+39) 011 222.55.12 - Fax (+39) 011 262.16.21
export@imper.it