TECHNICAL DATASHEET

VAPOBAR 1 AL/VV

Nature of product

Prefabricated waterproofing membrane obtained by coextrusion of a special steam-impermeable bitumen-polymer compound and of a reinforcement consisting of a sheet of pure aluminium and of a glass sheet. They are available in in 3 and 4 mm thicknesses.

They are produced in rolls, taped and supplied with Quality Control certificates. They comply with the requirements for CE marking where required. They do not contain asbestos, tar or other dangerous substances.

Intended use

The VAPOBAR 1 AL/VV membranes are specifically designed as steam barriers, below heat insulating elements, of insulated waterproofing roofing systems. Furthermore, with respect to use on roofs and in foundations, its use is indicated with reference to the following diagram ⁽¹⁾.

To identify the systems that can be obtained, consult the Technical Services of IMPER ITALIA srl.

PRODUCTS	FIELDS OF USE (1)										
			Ro (EN	Under-tile (EN 13859-1)	Steam control (EN 13970)	Foundations (EN 13969)					
	Exposed Roof gardens Under heavy-duty protectio										
	Single-ply U	Mult	Multi-ply		Cingle phy	Multi obr			Multi-ply		
		Upper	Lower	Root- resistant	Single-ply	Multi-ply					
VAPOBAR 1 AL/VV 3 mm								•			
VAPOBAR 1 AL/VV 4 mm								•			

(1) In compliance with the applicable AISPEC/SITEB-MBP Guidelines.







Application procedure

The substrate must be carefully cleaned from non-adhering or sharp parts. The next step is priming of all the surfaces to be covered with a suitable PRIMER applied in a single layer using a long-handled brush, roller or spray, with a consumption of $0.2 \div 0.3$ litres/m² and in any case variable according to the porosity of the substrate itself.

After drying, VAPOBAR 1 AL/VV is applied with the aid of a slight flame, taking care in particular that the joints are made by overlapping the adjacent sheets by at least 10 cm and that they are carefully sealed by means of thermofusion. The indications given here are purely indicative and require the applicator to adapt them on a case by case basis to the particular situation of the surface to be covered (slope, exposure, ventilation, monolithicity, etc.). In this regard, for more complete and detailed documentation regarding the application methods and creation of the entire stratigraphy, we recommend consulting the Technical Services of IMPER ITALIA srl which are in any case available to explore particular problems as well as to provide all the assistance necessary for optimum use of these materials.

TECHNICAL SPECIFICATIONS (1)										
Specifications	EN Standards	S Unit of Measure	Tolerances (1)	VAPOBAR 1 AL/VV						
Specifications	EN Stanuarus			3 MM	4 MM					
Roll dimensions	1848-1	m	2	10 :	(1					
Thickness	1849-1	mm	±5%	3	4					
Watertightness	1928-B	kPa	2	60	60					
Cold flexibility	1109	°C	≤	-1	-10					
Flow resistance at elevated temperature	1110	°C	2	12	120					
L/T tensile strength	12311-1	N/5cm	±20%	420 /	420 / 315					
L/T tensile elongation	12311-1	%	±2	2 /	2/2					
L/T dimensional stability	1107-1	%	≤	-	-					
Static puncture	12730	kg	2	1(10					
Dynamic puncture	12691-B	mm	2	-	-					
L/T tear resistance	12310-1	Ν	±30%	-	-					
Joint peel resistance	12316-1	N/5cm	±20 N	NDF	NDP (2)					
Joint cut resistance ⁽³⁾	12317-1	N/5cm	±20%	NDF	NDP ⁽²⁾					
Durability after aging::										
 Cold flexibility 	1296-1109	°C	+15°C	-	-					
• Flow resistance at elevated temperature	1296-1110	°C	-10°C	12	120					
• UV Ageing	1297	-	-	NDF	NDP (2)					
Watertightness	1296-1928	kPa	2	60	60					
Chemical resistance	-	-	-	NDF	NDP (2)					
L/T tensile strength	12311-1	N/5cm	±20%	-	-					
 L/T tensile elongation 	12311-1	%	±2	-	-					
Steam permeability	1931	μ	2	Absolu	Absolute ⁽⁵⁾					
Root resistance	13948		-	NDF	NDP ⁽²⁾					
External fire behaviour	13501-5	EC (4)	-	Fro	Froof					
Fire reaction	13501-1	EC (4)	-	F	F					

Notes: (1) In compliance with the applicable AISPEC/SITEB-MBP Guidelines.

(2) Characteristic not determined because it is not relevant for use.

(3) Declared value or failure away from joints.

- (4) Euroclass.
- (5) For the numeric calculation use $\mu \ge 500.000$.

Rev. 03 (06-22)

Considerando le diverse situazioni d'impiego dei prodotti e l'intervento di fattori da noi non dipendenti (supporti, condizioni di esercizio, in osservanza delle prescrizioni, ecc.), non è possibile alla IMPER ITALIA sri assumere responsabilità in merito ai risultati ottenuti. Il progresso unito alla costante ricerca dei massimi livelli prestazionali possono apportare - nel tempo - modificazioni alle informazioni contenute in questo stampato, senza che la IMPER ITALIA sri debba darne preavviso a tutti gli interessati.



Imper Italia srl - Via Rita Atria, 8 10079 Mappano (TO) Italy Tel (+39) 011 222.54.99 imper@imper.it · www.imper.it

Via Rita Atria, 9 · 10079 Mappano (TO) Italy · Tel (+39) 011 222.54.99 · export@imper.it