

EUROFLEX V UV**Description**

Flexible synthetic waterproofing membrane in plasticized vinyl chloride (PVC-P), obtained through a co-extrusion process. Suitable for waterproofing of tanks, channels and basins. Made with different colours on the two sides which allows you to identify any damage to the membrane during installation. High resistance to the attack of micro-organisms in soil, mechanical resistance. Resistance to low temperatures. Resistance to atmospheric agents and UV rays.

System certifications

QMS certification according to ISO 9001.

Product certifications

Regulation CPR 305/2011/EU.

Certificate No. 1370-CPR-1210, harmonised standard EN13361 - EN 13362

Fields of application**Specific use**

The EUROFLEX V UV membrane is suitable for the realisation of synthetic waterproofing systems for underground structures not directly exposed to ultraviolet radiation:

- basins.
- channels.
- storage tanks.

Application

The EUROFLEX V UV membranes are laid dry totally or partially independent with the aid of suitable fixings and/or profiles. The overlaps between the sheets are welded with automatic or manual hot welding.

Note: The installation must be carried out by qualified installers and approved by IMPER ITALIA.
Any accessories and finishing elements must be compatible and in any case manufactured or approved by IMPER ITALIA.

TECHNICAL FEATURES

Features	EN Standards	U.M.	Tolerance	Values			
Thickness	EN 1849-2	mm	(-5/+10%)	1,2	1,5	1,8	2,0
Mass per unit area	EN 1849-2	kg/m ²	(-5/+10%)	1,60	2,00	2,40	2,66
Cold flexibility	EN 495-5	°C	≤	-25			
Tensile strength	EN 12311-2	N/mm ²	± 2	17			
Elongation at break	EN 12311-2	%	± 10	300			
Water impermeability (24 h at 1 MPa)	EN 1928		-	No leaks			
Resistance to impact	EN 12691	mm	≥	500	750	800	1000
Resistance to static loading	EN 12730 EN 12236	kg kN	≥ ± 0,25	20 2,0	20 2,5	20 2,8	20 3,0
Microbiological resistance	EN 12225	-	-	Compliant			
Resistance to roots	UNI CEN/TS 14416	-	-	No penetration			
Resistance to oxidation	EN 14575	-	-	Pass the test			
Durability - Resistance to artificial light	EN 12224 (5000 h)	-	-	No surface cracks or significant variations of mechanical features			
Reaction to fire	EN 13501-1	Euroclass	-	E (*)			

(*) Internal report

PRODUCTION STANDARDS

Thickness (**)	mm	1,2	1,5	1,8	2,0
Width	m	2,10	2,10	2,10	2,10
Length (**)	m	25	25	20	20
Colour		Light grey / Black			

(**) Different thicknesses and lengths are available on demand and for minimum quantities.

Rev. 06 (05-22)

Considerando le diverse situazioni d'impiego dei prodotti e l'intervento di fattori da noi non dipendenti (supporti, condizioni di esercizio, in osservanza delle prescrizioni, ecc.), non è possibile alla IMPER ITALIA srl assumere responsabilità in merito ai risultati ottenuti. Il progresso unito alla costante ricerca dei massimi livelli prestazionali possono apportare - nel tempo - modificazioni alle informazioni contenute in questo stampato, senza che la IMPER ITALIA srl debba darne preavviso a tutti gli interessati.



Imper Italia srl - Via Rita Atria, 8
10079 Mappano (TO) Italy
Tel (+39) 011 222.54.99
imper@imper.it • www.imper.it