

SINTOFOIL ST WPS ST**Description ⁽¹⁾**

Synthetic waterproofing membrane produced by co-extruding a uniform highly flexible elastomerised polyolefin alloy. The membrane features contrasting colours on its upper and lower faces, providing a signal layer so that any damage occurring during or after installation will be immediately apparent. The upper side is structured for the implementation of injectable partitioned waterproofing systems that can be inspected. It is not UV resistant. SINTOFOIL ST WPS ST membranes comply with CE marking requirements, if applicable.

Note: (1) The membrane is equipped with specific accessories, to be requested explicitly.

System certifications

QMS certification according to ISO 9001.

This product can contribute to acquiring points in terms of LEED accreditation.

Fields of application**Specific use**

SINTOFOIL ST WPS ST membrane is recommended for waterproofing of structures:

- foundations.
- retaining walls.

Note: Given the versatility and reliability of SINTOFOIL membranes, other applications can be developed with the assistance of the IMPER ITALIA srl – Technical Services.

Application

Sintofoil membranes are designed for easy bonding with a hot air gun, as no adhesives or other materials of any kind are required. Design solutions and application methods are illustrated in the technical manual published by the Imper Synthetic Division. Waterproofing systems employing SINTOFOIL membranes should be laid by installers authorised by Imper Technical Services.

TECHNICAL FEATURES ⁽²⁾

Features	EN Standards	U.M.	Tolerance	Values
Standard thickness	1849-2	mm	(-5/+10%)	2
Appearance of upper surface				Structured
Density	1849-2	kg/m ²	(-5/+10%)	1.80
Tensile properties				
• Tensile strength L/T	12311-2	N/mm ²		15 / 15
• Elongation at break L/T	12311-2	%		600 / 600
Dimensional stability	1107-2	%		≤ 0.5
Cold flexibility	495-5	°C		≤ -40 ⁽³⁾
Tear resistance L/T	12310/1	N		650 / 600
Resistance to static loading	12730/B	kg		≥ 25
Water tightness (60 kPa)	1928			Absolute
Joint strength				
• Tensile strength	12317-2	N/cm		Compliant (specimen fails outside bond area)
• Peeling	12316-2	N/cm		≥ 58
Durability				
• Waterproofing after thermal ageing	1926-1928			Passes the test at 60 kPa
Resistance to algae and microorganisms	ISO 846 Level 2			Compliant
Root resistance	13948			Passes the test

Notes: (2) Tolerances as per EN 13967.
 (3) Not tested at lower temperatures.

PRODUCTION STANDARDS

Thickness ^(*)	mm	2,0
Width	m	2,10
Length ^(*)	m	20
Standard colour ^(*)		Beige / Black

^(*) Different thicknesses, lengths and colours are available on demand and for minimum quantities.

Rev. 02 (06-23)

Considerando le diverse situazioni d'impiego dei prodotti e l'intervento di fattori da noi non dipendenti (supporti, condizioni di esercizio, in osservanza delle prescrizioni, ecc.), non è possibile alla IMPER ITALIA srl assumere responsabilità in merito ai risultati ottenuti. Il progresso unito alla costante ricerca dei massimi livelli prestazionali possono apportare - nel tempo - modificazioni alle informazioni contenute in questo stampato, senza che la IMPER ITALIA srl debba darne preavviso a tutti gli interessati.



Imper Italia srl - Via Rita Atria, 8
 10079 Mappano (TO) Italy
 Tel (+39) 011 222.54.99
 imper@imper.it • www.imper.it