

PRIMER BIT PRO

Product description

Bituminous solvent-based primer for cementitious substrates.

Intended use

It is used as a roof and terrace preparer to be coated with bituminous membranes.

Technical specifications

Composition

Based on organic solvent bitumens.

Product type

Single-component, ready to use. The product must not be diluted.

Appearance

Black liquid.

Specific weight

g/dm³ 970 (±50)

Viscosity Ford 4 cup at 20°C

15 ÷ 25 sec

Storage at 20 °C

Keep the product in its tightly closed packaging. In these conditions the product is stable for over 2 years.

Performance

Membrane application time

Approximately 3 after application of PRIMER BIT PRO.

Coverage

4 ÷ 6 m² per litre, depending on absorption of substrate.

Product preparation

Always shake PRIMER BIT PRO before application.

Application

PRIMER BIT PRO can be applied with a paint brush, roller or large brush.

Wait until the product has dried before laying the bituminous membranes.

Do not smoke while applying PRIMER BIT PRO and avoid build-up of static electricity, flames or sparks.

PRIMER BIT PRO is highly sensitive to temperature due to its properties. Low temperatures increase the viscosity of the product and lengthen the drying time; conversely high temperatures, while not significantly affecting the viscosity of the product, shorten the drying time. Avoid applying PRIMER BIT PRO, however, to very hot surfaces because

this will significantly accelerate the filming process of the product with negative consequences on bonding and the adherence of the product to the laying surface.

Temperatures between 15°C and 30°C result in the best applications without significant variations in solvent release times.

The product contains solvents; it must, therefore, be applied in well-ventilated areas.

Packaging

5-Litre canisters

10-Litre canisters

20-Litre canisters

Attention: For use, carefully follow the safety instructions on the containers.

Rev. 02 (07-22)

Given the different situations in which the products are used and the intervention of external factors which do not depend on us (supports, operating conditions, compliance with regulations, etc.), IMPER ITALIA srl cannot assume responsibility for the results obtained. Moreover, progress and constant research for maximum performance levels may lead over time to the information contained in this document being changed. IMPER ITALIA srl is not required to provide prior notification to users of such changes.

